


Stick electrode, unalloyed, basic

Classifications					
EN ISO 2560-A	EN ISO 2560-B	AWS A5.1	AWS A5.1M		
E 42 3 B 1 2 H10	E 4916 AU	E7016	E4916		
Characteristics and typical fields of application					
Double covered basic electrode. Outstanding welding characteristics on AC and DC in all positions except the vertical down; stable arc, good radiographic soundness. Useable in handicraft and industry for field and workshop applications.					
Base materials					
S235JRG2 - S355J2, boiler steels P235GH, P265GH, P295GH, P355GH; Fine grained structural steels up to S355N; Pipe steels St 35, St 35.8, L210 - L360NB, GS-52, L290MB - L360MB; ASTM A27 and A36 Gr. all, A214, A242 Gr. 1-5, A266 Gr. 1, 2, 4, A283 Gr. A, B, C, D, A285 Gr. A, B, C, A299 Gr. A, B, A328, A366, A515 Gr. 60, 65, 70, A516 Gr. 55, A570 Gr. 30, 33, 36, 40, 45, A572 Gr. 42, 50, A606 Gr. all, A607 Gr. 45, A656 Gr. 50, 60, A668 Gr. A, B, A907 Gr. 30, 33, 36, 40, A841, A851 Gr. 1, 2, A935 Gr. 45, A936 Gr. 50; API 5 L Gr. B, X42-X56					
Typical analysis of all-weld metal (wt.-%)					
C	Mn	Si			
0.06	1.05	0.65			
Mechanical properties of all-weld metal – typical values (minimum values)					
Heat-treatment	Yield strength	Tensile strength	Elongation	Impact work	
	R <sub>p0.2</sub>	R <sub>m</sub>	A (L <sub>0</sub> =5d <sub>0</sub> )	ISO-V KV J	
	MPa	MPa	%	20°C	-30°C
u	420	550	22	80	50
sr	400	520	25	80	50
u: untreated, as welded sr: stress relieved 580 °C/2h / oven down to 300 °C / air					
Operating data					
	Polarity: DC (+) / AC	Redrying: 250 – 300 °C / 2 h	Ø (mm)	L mm	Amps A
			2.5	350	60 - 90
			3.2	350	95 - 150
			4.0	350	140 - 190
			5.0	450	140 - 190
Approvals					
TÜV (10573) • DB (10.132.57)					